

Silicone Resin impregnated Woven Glass 13001

Application

13001 Silicone resin impregnated woven glass fabric is used where a flexible high temperature insulating tape is required.

Technical data

Properties	Units	Typical Values	Test method
Nominal thickness	mm	0.13	IEC 60626-2
Total substance	g/m ²	175 ± 12	IEC 60626-2
Base glass fabric substance	g/m ²	123 ± 4	IEC 60626-2
Resin content	%	30 ± 3	IEC 60626-2
Tensile strength	N/cm	≥ 120	IEC 60626-2
Colour	-	Natural	-
Thermal class	°C	220 (C)	IEC 60085
Shelf life (minimum @20°C)*	Month	6	-

*Stored in a clean dry environment in the original sealed packaging out of direct sunlight

Availability	
Standard width, mm	10 - 965
Standard roll length	50m (Others available on request)
Standard core	76mm cardboard (Others available on request)

DISCLAIMER: All values indicated should be viewed as guideline values. Subject to changes. We do not accept any obligations or liabilities in respect of this information.